

REMARKS

This Amendment amends claim 14 in response to the Notice of Non-Compliant Amendment dated May 7, 2002. Claims 1-22 are pending. Claims 1-12 have been withdrawn from prosecution. Of the remaining claim, claim 14 is independent.

Attached hereto is a marked-up version of the changes made to the claim by the current Amendment. The attached page is captioned "**VERSIONS WITH MARKINGS TO SHOW CHANGES MADE**".

III. FORMAL MATTERS AND CONCLUSION


In view of the foregoing amendments and remarks, Applicants respectfully submit that the Application is in condition for allowance. Applicants respectfully request prompt reconsideration and allowance.

Should the Examiner believe that anything further is desirable to place the application into condition for allowance, Applicants invite the Examiner to contact the undersigned attorney at the telephone number listed below.

The Commissioner is hereby authorized to charge any deficiency in fees or to credit any overpayment in fees to Attorney's Deposit Account No. 50-0481.

Respectfully Submitted,

Date: 5/13/02



James E. Howard
Reg. No. 39,715

McGinn & Gibb, PLLC
8321 Old Courthouse Rd., Suite 200
Vienna, Virginia 22182
(703) 761-4100
Customer No. 21254

VERSION WITH MARKINGS TO SHOW CHANGES MADE

In the claims:

Please amend claim 14 as follows:

14. (Amended) A method for producing a transparent laminate comprising [steps of]:
preparing a transparent substrate;
depositing a high-refractive-index transparent thin film by a vacuum dry process;
depositing a silver transparent conductive thin film by a vacuum dry process;
repeating [said steps for] forming of the high-refractive-index transparent thin film
and the silver transparent conductive thin film at least three [or four] times to thereby form at
least three [or four] combination thin-film layers of the high-refractive-index transparent thin
film and the silver transparent conductive thin film successively laminated on a surface of
said transparent substrate; and
depositing another high-refractive-index transparent thin film on a surface of said
combination thin-film layer by the vacuum dry process,
wherein, when said silver transparent conductive thin films are deposited by the
vacuum dry process, temperature T (K) of said transparent substrate at the time of the
deposition of said films is set to be in a range $340 \leq T \leq 390$, and deposition rate R (nm/sec) of
said silver transparent conductive thin films is set to be $R = (1/40) \times (T - 300) \pm 0.5$.